

SCOTCH PAINT CORPORATION

FACTORY: 800-404-2878

FAX: 310-769-0436



4200 AQUA-SHEEN Acrylic Satin Enamel

DESCRIPTION

Aqua-Sheen will give maximum performance when used on properly prepared interior and exterior surfaces. Ideal for use on trim, sash, wood siding and primed metals. Aqua-sheen exhibits outstanding gloss retention, is high hiding and low odor. This product is also an ideal choice for commercial or rental property due to the excellent scrub and ability to be washed.

COLORS

White, Stock Colors and Light Tints.
Factory Custom colors 100 gallon minimum.

PACKAGING

Gallons, 5 Gallon pails

FINISH

Satin (Low-Sheen)

SUBSTRATES

Properly primed wood, metal, and masonry.

DRYING TIME

To touch – 1-2 hours

To recoat – 4-6 hours

Under normal weather conditions @70°F,
50 relative humidity

275 to 375 sq. ft. per gallon, depending on
surface texture and porosity.

SURFACE PREPARATION

All surfaces must be clean and dry and free
of dust, loose paint, and surface
contaminants that may impair adhesion.

V.O.C. Does not exceed 50 grams/liter

APPLICATION

Airless or conventional spray, brush or roll.

PRIMER

DRYWALL=	#PV101 PVA Sealer #63 Dynacoat Enamel Undercoat
BRICK =	#7509 "F" Stop #95 Busan Acrylic Primer #330 Draw-Tite Primer
WOOD, NEW =	#95 Busan Primer #63 Dynacoat Enamel Undercoat (Interior only)
PREVIOUSLY PAINTED =	#300 Bus-Stop 100% Acrylic Primer #97 100% Acrylic Primer
METAL: FERROUS =	#302 Rust-Stop White Primer #301 Rust-Stop Red Oxide Primer
NON-FERROUS =	#95 Busan Primer or #302 Rust Stop White Primer #300 Bus-Stop 100% Acrylic Primer #97 100% Acrylic Prime

THINNING

Small amount of Water if required.

CLEAN-UP Soap and warm water clean up.

SCOTCH PAINT CORPORATION
555 W. 189TH STREET
GARDENA, CA. 90248